

Agilus30



PolyJet Rubberlike Material

[Agilus30™](#) is a superior rubber-like [PolyJet™](#) photopolymer family ideal for advanced design verification and colorful [rapid prototyping](#). Get more durable, tear-resistant prototypes that can stand up to repeated flexing and bending and design validation. With a Shore A value of 30 in all Agilus30 versions you can accurately simulate the precise colorful look, feel and function of rubber-like products. 3D print rubber surrounds, overmolds, soft-touch colorful coatings, living hinges, jigs and fixtures, wearables, consumer goods, grips and seals with surface texture.

Mechanical Properties	Test Method	Value		
		Black / Translucent	White	Cyan/Magenta/Yellow
Tensile Strength	ASTM D-412	2.4 – 3.1 MPa (348 – 450 psi)	2.1-2.6 MPa (305 – 377 psi)	2.2 – 2.6MPa (319-377 psi)
Elongation at Break	ASTM D-412	220 – 270%	185 – 230%	315 - 335%
Compressive Set	ASTM D-395	6 – 7%	6 – 7%	6 – 7%
Tensile Tear Resistance	ASTM D-624	4 – 7 Kg/cm (22 – 39 lb/in)	4 – 7 Kg/cm (22 – 39 lb/in)	4.1-4.4 kg/cm (23-25 lb/in)

Other	Test Method	Value		
		Black / Translucent	White	Cyan/Magenta/Yellow
Shore Hardness	ASTM D-2240	30 – 35 Scale A	30 – 40 Scale A	28-33 Scale A
Polymerized Density	ASTM D-792	1.14 – 1.15 g/cm ³	1.14 – 1.15 g/cm ³	1.14 – 1.15 g/cm ³

System Availability	Layer Thickness Capability	Support Structure	Available Color
Objet260/350/500 Connex1/2/3™	High Speed mode: 30 microns (0.0012 in.)	SUP705 (WaterJet removable) SUP706B (soluble + WaterJet removable)	<input type="checkbox"/> Translucent
Stratasys J735™/ Stratasys J750™	High Speed mode: 27 microns (0.0011 in.)	SUP705 (WaterJet removable) SUP706B (soluble + WaterJet removable)	<input checked="" type="checkbox"/> Black <input type="checkbox"/> Translucent <input type="checkbox"/> White <input checked="" type="checkbox"/> Cyan <input checked="" type="checkbox"/> Magenta <input checked="" type="checkbox"/> Yellow
J4100™	High Speed mode: 27 microns (0.001 in.)	SUP705 (WaterJet removable)	<input checked="" type="checkbox"/> Black <input type="checkbox"/> Translucent
J826™ Prime / J835™ Prime / J850™ Prime / J850 Pro	High Quality mode: 14 microns (0.00055 in.) High Mix mode: 27 microns (0.001 in.) High Speed mode: 27 microns (0.0011 in.)	SUP705 (WaterJet removable) SUP706B (soluble + WaterJet removable)	<input checked="" type="checkbox"/> Black <input type="checkbox"/> Translucent <input type="checkbox"/> White <input checked="" type="checkbox"/> Cyan <input checked="" type="checkbox"/> Magenta <input checked="" type="checkbox"/> Yellow

USA - Headquarters

7665 Commerce Way
Eden Prairie, MN 55344, USA
+1 952 937 3000

EMEA

Airport Boulevard B 120
77836 Rheinmünster, Germany
+49 7229 7772 0



GET IN TOUCH.

www.stratasys.com/contact-us/locations

ISRAEL - Headquarters

1 Holtzman St., Science Park
PO Box 2496
Rehovot 76124, Israel
+972 74 745 4000

ASIA PACIFIC

7th Floor, C-BONS International Center
108 Wai Yip Street Kwun Tong Kowloon
Hong Kong, China
+ 852 3944 8888

stratasys.com

ISO 9001:2015 Certified

© 2022 Stratasys Ltd. All rights reserved. Stratasys, Stratasys signet, Agilus30, SUP705, SUP706B, Objet260 Connex3, Objet350 Connex3, Objet500 Connex3, Stratasys J735, Stratasys J750, J826, J835, J850, J4100 and PolyJet are trademarks or registered trademarks of Stratasys Ltd. and/or its subsidiaries or affiliates and may be registered in certain jurisdictions. All other trademarks belong to their respective owners. Product specifications subject to change without notice. MDS_PJ_Agilus30_CMY_A4_0422a

