



ULTEM 1010 Resin

HIGH-PERFORMANCE THERMOPLASTIC

FOR FORTUS 3D PRINTERS

ULTEM™ 1010 resin is a high-performance FDM® thermoplastic that offers excellent strength, thermal stability and the ability to withstand steam autoclaving. ULTEM 1010 resin is available in a general-purpose grade as well as a certified grade (CG) for those customers who want to take advantage of food-contact and bio-compatibility certifications for special applications including food production tools and custom medical applications. ULTEM 1010 resin offers the highest heat resistance, chemical resistance and tensile strength of any FDM thermoplastic and is ideal for aerospace and automotive applications.

MECHANICAL PROPERTIES ¹	TEST METHOD	ENGLISH		METRIC	
		XZ AXIS	ZX Axis	XZ Axis	ZX Axis
Tensile Strength, Yield (Type 1, 0.125", 0.2"/min)	ASTM D638	9,300 psi	5,990 psi	64 MPa	41 MPa
Tensile Strength, Ultimate (Type 1, 0.125", 0.2"/min)	ASTM D638	11,700 psi	7,000 psi	81 MPa	48 MPa
Tensile Modulus (Type 1, 0.125", 0.2"/min)	ASTM D638	402,000 psi	322,000 psi	2,770 MPa	2,200 MPa
Tensile Elongation at Break (Type 1, 0.125", 0.2"/min)	ASTM D638	3.3%	2.0%	3.3%	2.0%
Tensile Elongation at Yield (Type 1, 0.125", 0.2"/min)	ASTM D638	2.2%	1.5%	2.2%	1.5%
Flexural Strength (Method 1, 0.05"/min)	ASTM D790	21,000 psi	11,100 psi	144 MPa	77 MPa
Flexural Modulus (Method 1, 0.05"/min)	ASTM D790	409,000 psi	324,000 psi	2,820 MPa	2,230 MPa
Flexural Strain at Break (Method 1, 0.05"/min)	ASTM D790	No break	3.5%	No break	3.5%
IZOD Impact, notched (Method A, 23 °C)	ASTM D256	0.8 ft-lb/in	0.4 ft-lb/in	41 J/m	24 J/m
IZOD Impact, un-notched (Method A, 23 °C)	ASTM D256	6.1 ft-lb/in	2.6 ft-lb/in	326 J/m	138 J/m
Compressive Strength, Yield (Method 1, 0.05"/min)	ASTM D695	19,500 psi	15,100 psi	134 MPa	107 MPa
Compressive Strength, Ultimate (Method 1, 0.05"/min)	ASTM D695	No break	15,500 psi	No break	1,125 MPa
Compressive Modulus (Method 1, 0.05"/min)	ASTM D695	1,450,000 psi	305,000 psi	10,000 MPa	1,120 MPa

THERMAL PROPERTIES ²	TEST METHOD	ENGLISH	METRIC
Heat Deflection (HDT) @ 66 psi, 0.125" unannealed	ASTM D648	421 °F	216 °C
Heat Deflection (HDT) @ 264 psi, 0.125" unannealed	ASTM D648	415 °F	213 °C
Vicat Softening Temperature (Rate B/50)	ASTM D1525	416 °F	214 °C
Glass Transition Temperature (Tg)	DSC (SSYS)	419 °F	215 °C
Coefficient of Thermal Expansion	ASTM E831	26x10 ⁻⁶ in/(in·°F)	47 µm/(m·°C)
Coefficient of Thermal Expansion (xflow)	ASTM E831	25x10 ⁻⁶ in/(in·°F)	41 µm/(m·°C)
Melting Point	-----	Not Applicable ³	Not Applicable ³

ELECTRICAL PROPERTIES	TEST METHOD	VALUE RANGE
Volume Resistivity	ASTM D257	1.0 x10 ¹⁴ - 8.96x10 ¹⁵ ohm-cm
Dielectric Constant	ASTM D150-98	2.67
Dissipation Factor	ASTM D150-98	.001
Dielectric Strength	ASTM D149-09, Method A	240 V/mil

STRATASYS.COM



A GLOBAL LEADER IN APPLIED ADDITIVE TECHNOLOGY SOLUTIONS



ULTEM 1010 Resin

**HIGH-PERFORMANCE THERMOPLASTIC
FOR FORTUS 3D PRINTERS**

At the core:

Advanced FDM Technology

FDM (fused deposition modeling) technology works with engineering-grade thermoplastics to build strong, long-lasting and dimensionally stable parts with the best accuracy and repeatability of any 3D printing technology. These parts are tough enough to be used as advanced conceptual models, functional prototypes, manufacturing tools and production parts.

Meet production demands

FDM systems are as versatile and durable as the parts they produce. Advanced FDM 3D Printers boast the largest build envelopes and material capacities in their class, delivering longer, uninterrupted build times, bigger parts and higher quantities than other additive manufacturing systems, delivering high throughput, duty cycles and utilization rates.

Opening the way for new possibilities

FDM 3D Printers streamline processes from design through manufacturing, reducing costs and eliminating traditional barriers along the way. Industries can cut lead times and costs, products turn out better and get to market faster.

No special facilities needed

FDM 3D Printers are easy to operate and maintain compared to other additive fabrication systems because there are no messy powders or resins to handle and contain, and no special venting is required because FDM systems don't produce noxious fumes, chemicals or waste.

Other ²	Test Method	Value
Specific Gravity	ASTM D792	1.27
Rockwell Hardness	ASTM D785	109
Oxygen Index	ASTM D2863	0.44
Vertical Burn	FAR 25.853 (Test a (60s), passes at)	4 seconds
OSU Total Heat Release (2 min test, .060" thick)	FAR 25.853	35.7 kW min/m ²
Food Safety Certification ⁴	NSF 51	Certified
Bio-Compatibility Certification ⁴	ISO 10993/USP Class VI	Certified
BURN TESTING		
Horizontal Burn (15 sec)	14 CFR/FAR 25.853	Passed (.060" thick)
Vertical Burn (60 sec)	14 CFR/FAR 25.853	Passed (.060" thick)
Vertical Burn (12 sec)	14 CFR/FAR 25.853	Passed (.060" thick)
45° Ignition	14 CFR/FAR 25.853	Passed (.060" thick)
Heat Release	14 CFR/FAR 25.853	Passed (.060" thick)
NBS Smoke Density (flaming)	ASTM F814/E662	Passed (.060" thick)
NBS Smoke Density (non-flaming)	ASTM F814/E662	Passed (.060" thick)

System Availability	Layer Thickness Capability	Support Structure	Available Colors
Fortus 450mc™ Fortus 900mc™	0.010 inch (0.254 mm) 0.013 inch (0.333 mm) 0.020 inch (0.508 mm)*	Breakaway	■ Natural

* available on the Fortus 900mc only

The performance characteristics of these materials may vary according to application, operating conditions, or end use. The information presented are typical values intended for reference and comparison purposes only. They should not be used for design specifications or quality control purposes. End-use material performance can be impacted (+/-) by, but not limited to, part design, end-use conditions, test conditions, etc. Actual values will vary with build conditions. Tested parts were built on Fortus 400mc™ @ 0.010" (0.254 mm) slice. Product specifications are subject to change without notice.

The performance characteristics of these materials may vary according to application, operating conditions, or end use. Each user is responsible for determining that the Stratasys material is safe, lawful, and technically suitable for the intended application, as well as for identifying the proper disposal (or recycling) method consistent with applicable environmental laws and regulations. Stratasys makes no warranties of any kind, express or implied, including, but not limited to, the warranties of merchantability, fitness for a particular use, or warranty against patent infringement.

¹Build orientation is on side long edge.


²Literature value unless otherwise noted

³Due to amorphous nature, material does not display a melting point.

⁴Available for ULTEM 1010 CG (certified grade) canisters.

Orientation: See Stratasys Testing white paper for more detailed description of build orientations.

- XZ = X or "on edge"
- XY = Y or "flat"
- ZX = or "upright"



PROTOTECH.CO.KR

ISO 9001:2008 Certified

HEADQUARTERS

7665 Commerce Way, Eden Prairie, MN 55344
+1 888 480-3548 (US Toll Free)
+1 952 937-3000 (Intl)
+1 952 937-0070 (Fax)

()

가 1 19,
18 302
: 02) 6959-4113
: 02) 6959-4103